



Kneadaseal™ SL (Self-leveling) Electrical Sealing/Potting Compound

Product description

Kneadaseal SL is a self-leveling, epoxy sealing compound that hardens in less than 1 hour to provide water- and vaportight seals for cable fittings and electrical devices. Kneadaseal SL cures to a hard, rigid material that is resistant to hydrocarbons, ketones, alcohols and esters and has excellent adhesion to most substrates, including metal and ceramics. Kneadaseal SL is packed in a 225 ml. double-barrel cartridge for convenient dispensing, mixing and application. Its flowable consistency eliminates voids and ensures good wetting and coverage.

Basic uses

Kneadaseal SL can be applied with a double-barrel cartridge gun into areas between cable armor and conductors to form an effective seal. After about an hour, Kneadaseal SL hardens and forms a tenacious bond; full cure is achieved in 24 hours.

Benefits

- No shrinkage.
- Fast curing.
- Solvent-resistant.

Application limitations

- Generates heat during cure.
- Does not adhere to polyethylene, polypropylene or PTFE.
- Not for structural applications.

Cured color

Dark Gray.

Packaging

Available in a kit of one 6.75 fl. oz. (225 ml) double-barrel cartridge with 2 static mixers, packed 5 kits to a carton.

Applicable standards

Kneadaseal SL complies with the requirements of sealing compounds for Class I, Groups A, B, C and D; Class II, Groups E, F and G, in cable

Performance Data*

Properties	Results	Test Method
Uncured Properties		
Consistency	Flowable paste	
Work life at 75°F (24°C)	15 to 30 minutes	
Work life at 150°F (65°C)	5 to 10 minutes	
Non-volatile content	100%	
Cured Mechanical Properties		
Shore D hardness, full cure (24 hrs.)	85	
Lap shear tensile strength on steel (1" x 1" x 1/16")	300 lbs	ASTM D2240
Compressive strength	9,500 psi	
Shrinkage	<1%	
Upper temperature limits		ASTM D1002
Continuous	250°F (121°C)	
Intermittent	300°F (149°C)	
Lower temperature limit	-40°F (-40°C)	
Chemical resistance	Resistant to hydrocarbons, ketones, alcohols, halocarbons, esters, aqueous salt solutions, and dilute acids and bases	ASTM D495
Cured Electrical Properties		
Electrical resistance	30,000 megohms	ASTM D695
Volume resistivity	1x10 ¹⁴ ohm-cm	ASTM D149
Dielectric strength at 0.25 in.	400 v/mil	ASTM D257
Arc resistance	100 seconds	ASTM D257

* Typical properties are for information only, not for purposes of specification.

sealing fittings or lead seals for use in hazardous locations (requirements covering the class following exposure to acetone, ammonium hydroxide, ASTM Reference Fuel C, benzene, ethyl acetate, furfural, 2-nitropropane, methanol, methylethyl ketone, ethylenedichloride, diethyl-ether, acetic acid, n-hexane).

How to use

Surface preparation: To achieve optimum adhesion, surfaces must be cleaned free of grease, oil or dirt.

Mixing: Twist off cartridge cap and remove plug. Attach static mixer nozzle with cartridge cap and dispense material using a double-barrel cartridge gun.

Application: Apply to the surface within 15 minutes of mixing. The first few grams of mixed material should be discarded. Remove excess material before hardening begins. After 30 minutes the epoxy will harden and start to form a tenacious bond.

Shelf life: Six months from date of shipment when stored in original container in a dry area at temperatures below 80°F (27°C).

Availability and cost

Polymeric Systems, Inc., is a part of Whitford Worldwide. For more information, please contact Polymeric Systems or Whitford Ltd. at:

Polymeric Systems, Inc.
47 Park Avenue
Elverson, PA, USA 19520
800-CAULK IT (800-228-5548)
Tel: [1] 610-286-2500
Email: sales@polymericsystems.com
Website: polymericsystems.com

Health precautions

- Contains epoxy resin and amines.
- May be an eye irritant. For eye contact, flush with water for 15 minutes. Call a physician.
- May be a skin irritant. Avoid prolonged contact with skin. Use of thin plastic or rubber gloves is recommended for sensitive skin. For skin contact and after use, wash hands thoroughly with soap and water.
- May be harmful if swallowed. If swallowed, do not induce vomiting; call a physician.
- Keep out of reach of children.
- When sanding cured putty and substrate, use protective eye wear and dust mask.
- Turn off power when making electrical repairs.

For additional health and safety information, consult a Material Safety Data Sheet.

In the EU contact:

Whitford Ltd.
10, Christleton Court, Manor Park
Runcorn, Cheshire, UK WA7 1ST
Tel: [44] (1928) 571000
Email: salesuk@whitfordww.com
Website: whitfordww.com

NON-WARRANTY: ALL RECOMMENDATIONS, STATEMENTS AND TECHNICAL DATA CONTAINED HEREIN ARE BASED ON TESTS WE BELIEVE TO BE RELIABLE AND CORRECT, BUT ACCURACY AND COMPLETENESS OF SAID TESTS ARE NOT GUARANTEED AND ARE NOT TO BE CONSTRUED AS A WARRANTY, EITHER EXPRESS OR IMPLIED. USER SHALL RELY ON HIS OWN INFORMATION AND TESTS TO DETERMINE SUITABILITY OF THE PRODUCT FOR THE INTENDED USE, AND USER ASSUMES ALL RISK AND LIABILITY RESULTING FROM THIS USE OF THE PRODUCT. MANUFACTURER'S SOLE RESPONSIBILITY SHALL BE TO REPLACE THAT PORTION OF THE PRODUCT OF THE MANUFACTURER THAT PROVES TO BE DEFECTIVE. MANUFACTURER SHALL NOT BE LIABLE TO THE BUYER OR ANY THIRD PARTY FOR INJURY, LOSS OR DAMAGE DIRECTLY OR INDIRECTLY RESULTING FROM USE OF, OR INABILITY TO USE, THE PRODUCT. RECOMMENDATIONS OR STATEMENTS OTHER THAN THOSE CONTAINED IN A WRITTEN AGREEMENT SIGNED BY AN OFFICER OF THE MANUFACTURER SHALL NOT BE BINDING UPON THE MANUFACTURER.

2005--0109